

DuPont™ Delrin® 511CPE NC010 (Preliminary Data)

ACETAL RESIN

产品

Common features of Delrin® acetal resins include mechanical and physical properties such as high mechanical strength and rigidity, excellent fatigue and impact resistance, as well as resistance to moisture, gasoline, lubricants, solvents, and many other neutral chemicals. Delrin® acetal resins also have excellent dimensional stability and good electrical insulating characteristics. They are naturally resilient, self-lubricating, and available in a variety of colors and specialty grades.

Delrin® acetal resin typically is used in demanding applications in the automotive, domestic appliances, sports, industrial engineering, electronics, and consumer goods industries.

Delrin® 511CPE is a medium viscosity acetal homopolymer with enhanced crystallization for faster cycle times, excellent creep and fatigue resistance, and very low VOC emissions. Delrin® 511CPE provides improved thermal stability, excellent dimensional stability, low warpage, fewer voids, and improved productivity for injection moulding.

总说明	数值	单位	测试标准
树脂鉴别	POM	-	ISO 1043
产品标识码	POM	-	ISO 11469
流变性能	数值	单位	测试标准
熔体体积流动速度, MVR	13	cm³/10min	ISO 1133
温度	190	°C	ISO 1133
负荷	2.16	kg	ISO 1133
熔体质量流动速率	14	g/10min	ISO 1133
熔体质量流率, 温度	190	°C	ISO 1133
熔体质量流率, 载荷	2.16	kg	ISO 1133
模塑收缩率, 平行	1.8	%	ISO 294-4, 2577
模塑收缩率, 垂直	1.8	%	ISO 294-4, 2577
机械性能	数值	单位	测试标准
拉伸模量	3400	MPa	ISO 527-1/-2
屈服应力	77	MPa	ISO 527-1/-2
屈服伸长率	13	%	ISO 527-1/-2
名义断裂伸长率	25	%	ISO 527-1/-2
弯曲模量	3200	MPa	ISO 178
弯曲应力 (3.5%应变)	89	MPa	ISO 178
无缺口简支梁冲击强度, +23°C	235	kJ/m²	ISO 179/1eU
简支梁缺口冲击强度			ISO 179/1eA
+23°C	7	kJ/m²	
-30°C	6.5	kJ/m²	
洛氏硬度	95	-	ISO 2039-2
洛氏硬度, Rockwell	122	-	ISO 2039-2
热性能	数值	单位	测试标准
熔融温度, 10°C/min	178	°C	ISO 11357-1/-3
燃烧性能	数值	单位	测试标准
FMVSS Class	B	-	ISO 3795 (FMVSS 302)
燃烧速率, 厚度: 1毫米	<80	mm/min	ISO 3795 (FMVSS 302)
其它性能	数值	单位	测试标准
密度	1420	kg/m³	ISO 1183
熔体密度	1160	kg/m³	-
VDA性能	数值	单位	测试标准
挥发性	<2	mg/kg	VDA 275
注塑	数值	单位	测试标准
建议干燥	是	-	-
干燥时间, 除湿干燥机	2 - 4	h	-
最优熔体温度	205	°C	-
注塑 熔体温度	200	°C	-
注塑 熔体温度	210	°C	-
最优模具温度	90	°C	-
模具温度	80	°C	-
模具温度	100	°C	-

修订: 2019-04-15

Page: 1 of 6

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

China
Tel: +86 18551213137

Asia Pacific
Tel: +81 3 5521 8600

Europe/Middle East/Africa
Tel: +41 22 717 51 11



DuPont™ Delrin® 511CPE NC010 (Preliminary Data)

ACETAL RESIN

保压范围	80 - 100	MPa	-
保压时间	8	s/mm	-
回火时间, 可选	30	min/mm	-
回火温度	160	°C	-

典型数据

加工方法	• 注塑 • 异型材挤出成型	• 片材挤出成型 • 其它挤出成型	
供货形式	• 粒料		
地区供应	• 北美 • 欧洲	• 亚太 • 中南美洲	• 中东/非洲 • Global

成型

注塑

Drying is recommended, but not necessary for newly opened packaging stored in a dry location.

Follow the drying guidelines above in the following cases:

- If moisture is above the Processing Moisture Content recommendation,
 - When a resin container is damaged,
 - When the material is not properly stored in a dry place at room temperature
- or
- When packaging stays open for a significant time.




DuPont™ Delrin® 511CPE NC010 (Preliminary Data)


ACETAL RESIN

图表

粘度 - 剪切速度



剪切应力 - 剪切速度



修订：2019-04-15

Page: 3 of 6

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

China
Tel: +86 18551213137

Asia Pacific
Tel: +81 3 5521 8600

Europe/Middle East/Africa
Tel: +41 22 717 51 11




Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

DuPont™ Delrin® 511CPE NC010 (Preliminary Data)

ACETAL RESIN

应力 - 应变.



修订：2019-04-15

Page: 4 of 6

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

China
Tel: +86 18551213137

Asia Pacific
Tel: +81 3 5521 8600

Europe/Middle East/Africa
Tel: +41 22 717 51 11




Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

DuPont™ Delrin® 511CPE NC010 (Preliminary Data)

ACETAL RESIN

正割模量 - 应变.



修订：2019-04-15

Page: 5 of 6

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

China

Tel: +86 18551213137

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11




Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

DuPont™ Delrin® 511CPE NC010 (Preliminary Data)

ACETAL RESIN

拉伸模量 - 温度



以上是初步数据，可能会根据后面批次的测试数据产生变动。

联系杜邦以获得材料安全物性数据表、一般指南和/或其他关于排风、处理、清洗、干燥等的相关信息。除非特别指定，ISO机械性能测试样条厚度为4mm (Hytrel® 2mm英寸)，IEC电性能测试样品厚度为2mm，所有的ASTM性能测试样条厚度为3.2mm，测试温度为23°C。

这里阐明的信息是免费提供的，基于杜邦认为可靠的技术数据且，在材料性能的通常范围内。仅供具有专业技能的人使用，由其自行判断和承担风险。

这些数据不可以用作以建立技术说明规范，或者作为设计依据单独使用；我们提供处理预警信息是基于我们理解使用者会自行判断其特殊的使用条件不会对其产生健康或者安全危害。

由于产品使用和废弃的条件超出了本公司的控制范围，本公司对于本信息的使用不做任何保证，不论明示或暗示，亦不承担任何责任。

对于任何材料，制定规范前必须在终端使用条件下进行评估。

这里的任何信息不能作为使用专利或者侵犯专利权的许可。

警告：不要用于涉及永久植入人体的医疗应用。

如果需要其他医疗方面的应用，请联系杜邦销售代表并阅读医疗应用警告H-50103-5。

Copyright© 2019杜邦公司版权所有杜邦椭圆形商标，DuPont™, The miracles of science™ 以及所有标有® 或™ 的产品是杜邦公司或其分支机构关联公司的商标或者注册商标。

